

# Product Bulletin

## GF 100

### HIGH GLOSS OVERLAMINATING FILM

GF 100 Gloss Overlaminating Film is a pressure sensitive 3-mil high gloss PVC film with 200-4990 permanent acrylic adhesive on a smooth paper liner. This vinyl film offers protection from abrasion, moisture and other environmental exposures. It is laminated by the cold laminating process without the addition of heat.

|                                   |   |                  |
|-----------------------------------|---|------------------|
| <b>Applications</b>               | GF 100 gloss overlaminating vinyl film is designed to protect digital image prints and screen printed images for exhibit and display graphics. Can be used in most instances where an overlay with a high gloss finish is required. |                  |
| <b>Thickness</b>                  | Film  | 3.0 mils.        |
|                                   | Adhesive  | .8 to 1.0 mil.   |
|                                   | Liner   | 4.0 mils.        |
|                                   | (Thickness variance +/- 10%)  |                  |
| <b>Dimensional Stability</b>      | Good.   |                  |
| <b>Temperature Ranges</b>         | Minimum application temperature   | +40° F           |
|                                   | Service temperature range   | -40°F to +180°F. |
| <b>Expected Exterior Exposure</b> | This product is designed for interior applications. Exterior resistance has not been determined.  |                  |
| <b>Adhesion</b>                   | To stainless steel  | 48 oz/in.        |
|                                   | When tested according to PSTC-101 Method A procedures.  |                  |
|                                   | 24 hr. dwell at 70°F and 50% relative humidity.   |                  |
|                                   | Typical values. Individual values may vary. Test thoroughly before production.  |                  |
| <b>Light Transmission</b>         | Approximately 90% @ 550 nm  |                  |
| <b>Gloss</b>                      |   |                  |
| <b>60 ° Gardner</b>               | Initial > 80  |                  |
| <b>Storage Stability</b>          | 1-year shelf life when stored at 70°F and 50% relative humidity.  |                  |
| <b>Product Series</b>             | 100-38 38" x 150'   |                  |
|                                   | 100-51 51" x 150'   |                  |
|                                   | 100-54 54" x 150'   |                  |
|                                   | 100-61 61" x 150'   |                  |



*Manufacturers of  
Pressure Sensitive Films*

309 S. Union • P.O. Box 158 • Sparta, Michigan 49345 • (616) 887-7387 • (800)253-3664 • FAX (616)887-0537  
Web Site: [www.generalformulations.com](http://www.generalformulations.com) • e-mail: [info@generalformulations.com](mailto:info@generalformulations.com)

We believe the information on this product to be accurate. However, since we cannot anticipate or control the conditions under which this information or our products may be used, we cannot guarantee results obtained through their use. Tests of our products should be made by users to determine the suitability of these products for a specific purpose. The products are sold without warranty, either express or implied. The purchaser should refer to General Formulations, Inc's Price List for Terms and Conditions or Sale, Including Disclaimer of Warranties and Limitation of Liability.