

# Whiteboard Dryapply ASLAN WBL 995



## High quality whiteboard film for easy dry applications

The self-adhesive whiteboard film turns every surface into a writable whiteboard. The highly scratch resistant surface ensures that writings can be wiped off dry without leaving any shadows or ghostings. Finest air release channels allow air bubbles to be wiped out with ease and make the application fast and easy.

For additional information please contact our technical advisory service:  
**+49 (0) 22 04. 7 08-80**

## Construction

face-film:	Polyester/PVC – compound, white glossy	
thickness:	~ 150 µm	
adhesive:	acrylic pressure adhesive	square quantity: ~ 25 g/m <sup>2</sup>
release liner:	structured silicone cardboard both sided PE coated	square weight: ~ 135 g/m <sup>2</sup>

## Characteristics

adhesive strength: (ASTMD-903)	immediately after 1 week	~ 3 N/25 mm ~ 5 N/25 mm
dimensional stability:	applied onto aluminum after 48 hours stored at 70 °C (25 x 25 cm)	max. -0.45 %
chemical resistance:	In a preece test of 24 hours the applied film is resistant to most petroleum based oils, greases and aliphatic solvents, mild acids, alkalis and salts.	
temperature:	application temperature: service temperature range:	min. 15°C -30 °C up to +80 °C
durability:	up to 5 years outdoors, with vertical exposure, in central-European climate.	

**ASLAN, Schwarz GmbH & Co. KG**  
Oberauel 2 · 51491 Overath · Germany  
**phone** +49 (0) 2204. 708 80 · **fax** +49 (0) 2204. 708 50  
**e-mail** info@ASLAN-Schwarz.com



[www.ASLAN-Schwarz.com](http://www.ASLAN-Schwarz.com)

**ASLAN**   
EXPERTISE IN SELF-ADHESIVE FILMS

# Whiteboard Dryapply ASLAN WBL 995



## Processing

<b>application:</b>	Dry application only. To exclude that tunneling might occur, the self-adhesive films should only be cut face down. In case, the cut film is rolled up for storage or transportation, this should be done in the same direction of winding it was delivered in, in a generous radius (> 5 cm) and ideally onto a core.
<b>cleaning:</b>	Writings with whiteboard markers can be wiped off dry easily without leaving any ghostings. If by mistake pens with solvent paints have been used the writings can be wiped off with alcohol.
<b>storage life:</b>	Before application the films can be stored for minimum 3 years from date of production. The film must be stored at room temperature (15-25 °C) and a relative humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed 'hanging' racks.

### State: 04|2017

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test the suitability of our products for the intended purpose.

The quality of our products is regularly examined, upgraded and developed. We take the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of our products in accordance with our latest knowledge.

### ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany

**phone** +49 (0) 2204. 708 80 · **fax** +49 (0) 2204. 708 50

**e-mail** info@ASLAN-Schwarz.com



[www.ASLAN-Schwarz.com](http://www.ASLAN-Schwarz.com)

**ASLAN**®

EXPERTISE IN SELF-ADHESIVE FILMS